

RESEARCH HIGHLIGHT

Near-room-temperature superconductivity in hydrogen sulfide

Yanming Ma

NPG Asia Materials (2016) 8, e236; doi:10.1038/am.2015.147; published online 22 January 2016

Room-temperature superconductivity has been a long-held dream and an area of intensive research, despite the common belief—based on more than a century of work in the field—that the highest temperature at which phonon-mediated superconductors can work is only 40 K. Drozdov *et al.*¹ of the Max Planck Institute in Mainz, Germany, has reported surpassing this traditional limit, demonstrating that hydrogen sulfide under a pressure of 1.5 million atmospheres exhibits phonon-mediated superconductivity at 203 K. This discovery opens the door to achieving room-temperature superconductivity in compressed hydrogen-rich materials.

In 1911 a Dutch physicist, Heike Kamerlingh Onnes, observed superconductivity (i.e., conduction of electricity without resistance) below 4 K in solid mercury. Since then, considerable attention has been paid to the goal of achieving superconductivity at ever-higher temperatures for practical use.

In the following century, research effort was devoted mainly to unconventional cuprate and iron-based superconductors, whose superconducting mechanism is not yet fully understood. These putative ‘high-temperature’ superconductors were believed to represent the sole hope for achieving room-temperature superconductivity. Conventional superconductors follow the Bardeen–Cooper–Schrieffer theory;² their superconductivity arises from their acting as superfluids via electron pairing mediated by the exchange of phonons. The highest superconducting transition temperature of 39 K was observed in MgB₂, a finding that led physicists to believe that conventional superconductivity cannot occur above 40 K.

The search for superconductivity in pressurized hydrogen-rich materials was initiated by Ashcroft,³

who proposed that hydrogen-rich materials, once metalized, have the potential to become high-temperature superconductors. Hydrogen, having the lightest atomic mass, gives these materials the high Debye temperatures necessary for high-temperature phonon-mediated superconductivity.

Solid hydrogen sulfide (H₂S) has not previously been considered a superconductor because, upon metallization under pressure, it was believed to dissociate into its constituent elements. Recent theoretical work⁴ indicated that such dissociation would not occur and predicted that H₂S pressurized at 1.6 million atmospheres would show superconductivity at temperatures above 80 K. This led to the practical work of Drozdov *et al.*,¹ who found that H₂S compressed in a diamond anvil cell exhibited two astonishing superconductive states at pressures above 1 million atmospheres: the superconductivity ranging from 30 to 150 K measured in the low-temperature runs (Fig. 1)¹ relates to H₂S, as it is consistent with calculations;⁴ the highest superconductivity of 203 K was achieved in samples annealed at the room temperature (Fig. 2).¹ The transition temperature showed a pronounced isotope effect, indicating phonon-mediated superconductivity. The 203 K superconductivity is probably associated with a stoichiometric change to H₃S that was predicted to be a high-temperature superconductor⁵ due to the decomposition of H₂S under pressure.

The work by Drozdov *et al.*¹ has disproved the conventional wisdom regarding the 40 K superconduction limit of phonon-mediated superconductors, and, more significantly, it supports the general idea of high-temperature superconductivity in hydrogen-rich materials. A broad range of hydrogen-rich materials is ready for exploration,

and they offer the tantalizing prospect of the imminent development of room-temperature superconductors.

CONFLICT OF INTEREST

The author declares no conflict of interest.

- 1 Drozdov, A. P., Eremets, M. I., Troyan, I. A., Ksenofontov, V. & Shylin, S. I. Conventional superconductivity at 203 Kelvin at high pressures in the sulfur hydride system. *Nature* **525**, 73 (2015).
- 2 Bardeen, J., Cooper, L. N. & Schrieffer, J. R. Microscopic theory of superconductivity. *Phys. Rev.* **106**, 162–164 (1957).
- 3 Ashcroft, N. W. Hydrogen dominant metallic alloys: high temperature superconductors? *Phys. Rev. Lett.* **92**, 187002 (2004).
- 4 Li, Y., Hao, J., Liu, H., Li, Y. & Ma, Y. The metallization and superconductivity of dense hydrogen sulfide. *J. Chem. Phys.* **140**, 174712 (2014).
- 5 Duan, D., Liu, Y., Tian, F., Li, D., Huang, X., Zhao, Z., Yu, H., Liu, B., Tian, W. & Cui, T. Pressure-induced metallization of dense (H₂S)₂H₂ with high-T_c superconductivity. *Sci. Rep.* **4**, 6968 (2014).



This work is licensed under a Creative Commons Attribution 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder to reproduce the material. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>